



Eurowall[®] Cavity



Eurowall Cavity is a thermal insulation board. Its core consists out of polyisocyanurate PIR foam. The board is faced with a gas diffusion tight multilayer foil on both sides. Grid pattern on both sides.

Application(s)

Thermal insulation of partial fill cavity walls

Board

Description	Value	Unit	Tolerances	Standard
Dimensions				
Length	1200	mm		
Width	450	mm		
Thickness range	20-160	mm	T2	EN 823
Density (core volume weight)	± 30	kg/m ³		

Appearance

Facing	Gas diffusion tight multilayer foil on both sides. Grid pattern on both sides.
Edge finishing	Straight edges on four sides.

Essential Characteristics

Description	Standard	EN code	Value	Unit
Thermal conductivity (declared value)				
All thicknesses	EN 13165	λ_D	0.022	W/m.K
Fire behaviour				
Reaction to fire (product as such)	EN 13501-1	Euroclass	F	
Emissivity*		ϵ	0.05	

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user. An older version of this technical datasheet can be requested via technicalservices@recticel.com in case required.

Recticel Insulation

Enterprise Way, Whittle Road, Meir Park, Stoke-on-Trent, Staffordshire, ST3 7UN, UK

www.recticelinsulation.com

FEEL
GOOD
INSIDE



Eurowall[®] Cavity

Insulation Values

Thickness (mm)	λ_D -value (W/mK)	R _D -value (m ² K/W)
30	0.022	1.35
40	0.022	1.80
50	0.022	2.25
60	0.022	2.70
70	0.022	3.15
75	0.022	3.40
80	0.022	3.60
90	0.022	4.05
100	0.022	4.50

Standards & Certificates

Standards

Product standard	EN 13165:2012 + A2:2016
Production	ISO 9001:2015
Environmental management	ISO 14001:2015

Certificates

BBA	02/3908	(20-160mm)
PEFC	100% PEFC - certificate number: CU-PEFC-867959	

Other / Miscellaneous

Production plant

Recticel Ltd. Enterprise way, Meir Park – Stoke-On-Trent, ST3 7UN - UK

Storage/handling

Stock dry and protected from direct sunlight

* Emissivity can only be taken into account in the thermal calculation of a wall when the insulation is installed in a non-ventilated cavity.

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user. An older version of this technical datasheet can be requested via technicalservices@recticel.com in case required.

Recticel Insulation

Enterprise Way, Whittle Road, Meir Park, Stoke-on-Trent, Staffordshire, ST3 7UN, UK

www.recticelinsulation.com

FEEL
GOOD
INSIDE

