

### Product Description & Application

Single-sided DuPont™ Tyvek® (HD-PE) with high coat weight water based modified acrylic adhesive and a paper interliner. DuPont™ Tyvek® Acrylic Tape is suitable for sealing membrane laps, but particularly suitable for making good around penetrations and for damage repair for all Tyvek® Underlays and Vapour Control Layers.

### Specifications

| PROPERTY            | VALUE                |
|---------------------|----------------------|
| Stylename           | 2060B                |
| Colour              | White                |
| Thickness           | 300 µm               |
| Basis weight        | 220 g/m <sup>2</sup> |
| Temperature range   | -40 °C to 100 °C     |
| Tensile strength    | 300 N/5cm            |
| Elongation at break | 15 %                 |
| Peel adhesion       | 25 N/25mm            |

### Use and Care Recommendations

- Product is designed for the building industry. Tyvek® Acrylic Tape has a high immediate tack and excellent adhesion onto Tyvek® and a wide range of plastic materials (e.g. non-woven, film,...).
- Users must check that the Tyvek® Acrylic Tape is suitable for the support (adhesion, chemical compatibility, staining,...).
- The resistance to ageing, water, humidity, environmental cycling and chemicals is excellent.
- The recommended application temperature is > 0 °C. The application should be done on a dry and clean surface (no dust, no grease, no solvent,...).
- Conditions: store rolls in their initial packaging, flat, in a clean and dry place. Storage temperature between +10 °C & 30 °C

Date: January 15, 2014

DuPont de Nemours  
(Luxembourg) S.à r.l.  
Rue General Patton,  
L - 2984 Luxembourg  
Tel.: +352 3666 5885  
tyvek.info@lux.dupont.com

[www.construction.tyvek.com](http://www.construction.tyvek.com)

This information corresponds to our current knowledge on the subject. It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any application other than the application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liabilities in connection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature.

